

Hybrid organic–inorganic materials for novel photonic applications

Partha P. Banerjee,^{1,*} Dean R. Evans,² Wei Lee,³ Victor Yu. Reshetnyak,⁴ and Nelson Tansu⁵

¹Department of Electrical and Computer Engineering, and Electro-Optics Program, University of Dayton, Dayton, Ohio 45469, USA

²Air Force Research Laboratory, Materials and Manufacturing Directorate, Wright-Patterson Air Force Base, Ohio 45433, USA

³College of Photonics, National Chiao Tung University, Guiren District, Tainan 71150, Taiwan

⁴Physics Faculty, National Taras Shevchenko University of Kyiv, Kyiv 01601, Ukraine

⁵Department of Electrical and Computer Engineering, Center for Photonics and Nanoelectronics, Lehigh University, Bethlehem, Pennsylvania 18015, USA

*Corresponding author: pbanerjee1@udayton.edu

Received 25 June 2013;

posted 25 June 2013 (Doc. ID 192915); published 31 July 2013

This novel joint feature issue on “Hybrid organic–inorganic materials for photonic applications” in *Applied Optics* and *Optics Materials Express* comprises 14 papers on liquid crystals, polymers, photoconductive materials, and gratings and filters. It is hoped that this feature issue encourages and stimulates further research into hybrid materials with enhanced linear and nonlinear optical properties, their mechanisms of operation, and their applications. © 2013 Optical Society of America

OCIS codes: (160.2100) Electro-optical materials; (160.3710) Liquid crystals; (160.5320) Photo-refractive materials; (160.5470) Polymers; (160.1245) Artificially engineered materials; (160.4236) Nanomaterials.

<http://dx.doi.org/10.1364/AO.52.000HM1>

It is well-known that many natural materials consist of inorganic and organic building blocks where the inorganic part provides mechanical strength and an overall structure to the natural objects, while the organic part delivers bonding between the inorganic building blocks and/or the soft tissue. The most obvious advantage of inorganic–organic hybrids is that they can favorably combine the often dissimilar properties of organic and inorganic components in one material. The study of such materials has encouraged many materials researchers to use a biomimetic approach to artificially manufacture many

novel materials for use in applications, such as scratch-resistant coatings, dental fillings, fire-retardants, super-capacitors and energy production and storage devices, etc. Electro-optical applications of hybrids include light-emitting diodes, photodiodes, solar cells, sensors (including plasmonic and biosensors), field-effect transistors, and efficient nonlinear optical devices. Other novel optical applications include organic–inorganic-based meta and plasmonic materials for imaging and sensing.

Hybridization of organic and inorganic materials also opens up yet another new and exciting area in applied optics. The various forms of hybrids in this special issue have organic and inorganic components, where the inorganics modify the optical and electric properties of the organics. In addition, the organic

matrix may provide a flexible structure as well as order/structure to the nanomaterials [i.e., nanoparticles, liquid crystals (LCs), etc.]. The optical and electric properties of LCs have been shown to be enhanced using nanoparticles. Furthermore, it has also been reported that LCs can be strongly influenced by polymer materials in terms of structuring, ordering, and stabilizing. Outside their role in LC devices, polymers themselves can be hybridized with nanomaterials, modifying the refractive index, birefringence, and source of charge donors/acceptors. Devices exploring these phenomena may find applications in optical beam coupling, optical switches, spatial and temporal filters, tunable photonic crystals, beam shaping, optical displays, and hybridized light valve technologies.

Specifically, this feature issue consists of 14 papers comprising four sections: liquid crystals (Lorenz *et al.* [1], Rudzki *et al.* [2], Garbovskiy and Glushchenko [3], Lavrič *et al.* [4], and Yaroshchuk *et al.* [5]); polymers (Nabil *et al.* [6], Minasyan and Galstian [7], Uklein *et al.* [8], Nazarova *et al.* [9] and Sassa *et al.* [10]); photoconductive materials (Bortolozzo *et al.* [11] and Mercado-Zúñiga *et al.* [12]); and gratings and filters (Sheremet *et al.* [13] and Danaeifar *et al.* [14]). The papers by Uklein *et al.* and Sassa *et al.* appear in *Optical Materials Express*, while the rest appear in *Applied Optics*.

In the first section, Lorenz *et al.* investigated the influence of ferroelectric nanoparticles on the realignment of the LC director upon the application of an electric field. In this invited paper, LC nano-dispersion with BaTiO₃ ferroelectric nanoparticles showed a more pronounced reorientation with a reduced threshold voltage compared to the undoped LC. Rudzki *et al.* studied the influence of various-size harvested barium titanate nanoparticles on the properties of ferroelectric liquid crystal (FLC) using electro-optical and dielectric methods. There is a reduction of the switching time with decrease of BaTiO₃ particle size and the (Goldstone mode) viscosity. Garbovskiy and Glushchenko explore how optical and BaTiO₃ and PbTiO₃ ferroelectric properties of stressed ferroelectric nanoparticles set a limit on the performance of optical and electro-optical devices. Lavrič *et al.* present a theoretical model accounting for the impact of anisotropic MoS₂ nanoparticles on the blue phase stability region in chiral LC, and validate the model by high-resolution calorimetric and optical measurements. This study revealed that the geometry of the nanoplatelets played an important role in the stabilization of different blue phase structures. Yaroshchuk *et al.* investigated photoresponsive electro-optical composites comprising cholesteric LC doped with carbon nanotubes, demonstrating a dual-mode operation with the optical switching between reversible and memory mode. They showed that LC composites with homeotropic anchoring exhibit a transition from fingerprint texture to homeotropic nematic texture in the course of a photoinduced unwinding of the cholesteric helix.

Nabil *et al.* applied polymer dispersed liquid crystal (PDLC) as cladding material in a polymer-based

variable optical attenuator. The PDLC-based waveguide was electro-optically modified at low operating voltages without the need of alignment layer as in the case of LC. Minasyan and Galstian created surface polymer stabilized structures using dual frequency controlled LC with thin reactive mesogen films. These devices greatly improved contrast and polarization independence of light scattering, and achieved very short transition times when switching from low to high frequency. Uklein *et al.* reported on photoinduced modifications of the refractive index of nanoparticulate TiO₂-pHEMA organic-inorganic hybrids. Their results suggested that refraction index variations of the order of 0.005 are attainable, making these materials candidates for applications in optoelectronics. Nazarova *et al.* synthesized an anisotropic organic/inorganic nanocomposite material using SiO₂ nanoparticles in a side-chain azopolymer. They observed about 20% enhancement of the photoinduced birefringence in these composite materials compared to nondoped samples. Sassa *et al.* studied the influence of a transient dark current on the buildup dynamics of photorefractive polymer index gratings. They concluded that transient dark current flow is an important factor to be considered to optimize conditions for pulsed voltage-assisted PR effects.

Bortolozzo *et al.* developed a LC light-valve (LCLV) and a self-defocusing medium for near-infrared applications using GaAs:Cr photoconductive substrates. The LCLV displays an efficient behavior as an optically addressable transmissive spatial light modulator, with potential future applications in interferometric systems or in thermal sensors due to the large Kerr-like nonlinear coefficient. Mercado-Zúñiga *et al.* developed a photoconductive logic gate based on platinum decorated carbon nanotubes, and characterized the electrical and nonlinear optical properties of these materials. The photoconductive logic gate function OR was experimentally demonstrated.

In the last section of this joint special issue, the invited paper by Sheremet *et al.* showed the results of recording polarization gratings in a combined LC cell made of a substrate covered with a photosensitive chalcogenide orientation layer and a reference substrate covered with a rubbed polyimide film. They showed that the application of an ac-field caused a strong increase of the first order diffraction efficiency. Danaeifar *et al.* demonstrated that a 2D sheet of graphene can be used as a simple band-pass filter in terahertz and infrared frequencies. The effects of various material and device parameters on surface plasmon polariton waves and filter specifications were numerically depicted. This material can operate in a wide frequency range, with potential uses as telecommunication transducers and infrared cameras.

In light of the rapid progress in this area, it is hoped that this novel joint feature issue in *Applied Optics* and *Optical Materials Express*

encourages and stimulates further research into hybrid materials, their mechanisms of operation, and their applications. The editors feel that the future of optical hybrid materials will continue to bring to fruition new materials with enhanced linear and nonlinear optical properties, opening new doors to unexplored application and the improvement of performance of current technologies. Potential areas to explore, in addition to the numerous areas explored in this Feature Issue, are optical bio-sensors, optical metamaterials, plasmonics, and interactions at the boundaries of the organic and inorganic components of hybridized materials.

Feature editors

Partha P. Banerjee, University of Dayton, USA
Dean R. Evans, Air Force Research Laboratory, USA
Wei Lee, National Chiao Tung University, Taiwan
Victor Yu. Reshetnyak, National Taras Shevchenko
University of Kyiv, Ukraine
Nelson Tansu, Lehigh University, USA

References

1. A. Lorenz, N. Zimmermann, S. Kumar, D. R. Evans, G. Cook, M. Fernández Martínez, and H.-S. Kitzerow, "X-ray scattering of nematic liquid crystal nanodispersion with negative dielectric anisotropy [Invited]," *Appl. Opt.* **52**, E1–E5 (2013).
2. A. Rudzki, D. R. Evans, G. Cook, and W. Haase, "Size dependence of harvested BaTiO₃ nanoparticles on the electro-optic and dielectric properties of ferroelectric liquid crystal nanocolloids," *Appl. Opt.* **52**, E6–E14 (2013).
3. Y. Garbovskiy and A. Glushchenko, "Optical/ferroelectric characterization of BaTiO₃ and PbTiO₃ colloidal nanoparticles and their applications in hybrid materials technologies," *Appl. Opt.* **52**, E34–E39 (2013).
4. M. Lavrič, G. Cordoyiannis, S. Kralj, V. Tzitzios, G. Nounesis, and Z. Kutnjak, "Effect of anisotropic MoS₂ nanoparticles on the blue phase range of a chiral liquid crystal," *Appl. Opt.* **52**, E47–E52 (2013).
5. O. Yaroshchuk, S. Tomylko, I. Gvozdoyskyy, and R. Yamaguchi, "Cholesteric liquid crystal–carbon nanotube composites with photo-settable reversible and memory electro-optic modes," *Appl. Opt.* **52**, E53–E59 (2013).
6. G. Nabil, W. F. Ho, and H. P. Chan, "Experimental study on the performance of a variable optical attenuator using polymer dispersed liquid crystal," *Appl. Opt.* **52**, E15–E21 (2013).
7. A. Minasyan and T. Galstian, "Surface-polymer stabilized liquid crystals with dual-frequency control," *Appl. Opt.* **52**, E60–E67 (2013).
8. A. Uklein, P. Gorbovyi, M. Traore, L. Museur, and A. Kanaev, "Photo-induced refraction of nanoparticulate organic-inorganic TiO₂-pHEMA hybrids," *Opt. Mater. Express* **3**, 533–545 (2013).
9. D. Nazarova, L. Nedelchev, P. Sharlandjiev, and V. Dragostinova, "Anisotropic hybrid organic/inorganic (azopolymer/SiO₂ NP) materials with enhanced photoinduced birefringence," *Appl. Opt.* **52**, E28–E33 (2013).
10. T. Sassa, T. Fujihara, J.-I. Mamiya, and M. Kawamoto, "Effects of transient dark currents on the buildup dynamics of refractive index changes in photorefractive polymers excited by pulsed voltage," *Opt. Mater. Express* **3**, 472–479 (2013).
11. U. Bortolozzo, S. Residori, and J.-P. Huignard, "Transmissive liquid crystal light-valve for near-infrared applications," *Appl. Opt.* **52**, E73–E77 (2013).
12. C. Mercado-Zúñiga, J. R. Vargas-García, F. Cervantes-Sodi, M. Trejo-Valdez, R. Torres-Martínez, and C. Torres-Torres, "Photoconductive logic gate based on platinum decorated carbon nanotubes," *Appl. Opt.* **52**, E22–E27 (2013).
13. N. Sheremet, Y. Kurioz, K. Slyusarenko, M. Trunov, and Y. Reznikov, "Recording of polarization holograms in a liquid crystal cell with a photosensitive chalcogenide orientation layer [Invited]," *Appl. Opt.* **52**, E40–E46 (2013).
14. M. Danaeifar, N. Granpayeh, A. Mohammadi, and A. Setayesh, "Graphene-based tunable terahertz and infrared band-pass filter," *Appl. Opt.* **52**, E68–E72 (2013).