

Contents

Abstract (in Chinese)	
Abstract (in English)	
Acknowledgement	
Contents	
List of figures	XI
Chapter 1 Introduction	1
1-1 A Brief History of Vertical-Cavity Surface-Emitting Laser (VCSEL)	1
1-2 Fabricating Processes of VCSEL Devices	4
1-2-1 Gain-guiding mechanism	6
1-2-2 Index-guiding mechanism	8
1-2-3 Hybrid-guiding mechanism	16
1-3 Overview of this Thesis	18
References	21
Chapter 2 Proton-implanted VCSEL with Transparent Contact	25
2-1 Literature survey	25
2-2 Experiment	27
2-3 Results and Discussions	30
2-4 Summary	34
References	35
Chapter 3 Si⁺-implanted VCSEL (Index-guided VCSEL)	37
3-1 Literature survey	37
3-2 Device structure and fabrication	38
3-3 VCSEL performance	40
3-4 VCSEL reliability	44
3-5 Summary	44
References	46
Chapter 4 High Speed Oxygen-implanted VCSEL	49
4-1 Literature survey	50
4-2 Device structure and fabrication	51
4-3 Results and Discussion	52
4-4 Summary	54
References	55
Chapter 5 Proton-implanted VCSELs with Photonic Crystal	59
5-1 Literature survey and Background	59
5-2 Experiment	62
5-3 Results and Discussions	65
5-4 Summary	69
References	70

Chapter 6	Conclusion	71
6-1	Conclusion	71
6-2	Future work	72
6-2-1	Long-wavelength VCSEL	72
6-2-2	Oxidation developed in GaN-based material	75
	<i>References</i>	77
Vita		78
Publication List		79



List of figures

Chapter 1

Figure 1-1	Schematic structure of (a) edge emitting laser, (b) vertical-cavity surface-emitting laser.	3
Figure 1-2	Various choices of the active region materials for VCSEL	5
Figure 1-3	Schematic diagram of a gain-guiding VCSEL with circular electrode to confine injection carrier concentration into the active layer.	6
Figure 1-4	Schematic diagram of a gain-guided VCSEL ion implantation regions to confined injection carrier concentration into the active region.	8
Figure 1-5	Schematic diagram of aorposted VCSEL (index-guided structure); active layer (a) below and (b) within the airposted column.	9
Figure 1-6	Schematic diagram of aorposted VCSEL (index-guided structure) with intracavity design.	10
Figure 1-7	Schematic diagram of a buried heterostructure VCSEL (index-guided structure) with injection carrier concentration strongly confined uniformly inside the active region.	11
Figure 1-8	(a) Schematic diagram of an antiguided VCSEL; (b) the corresponding profile of effective refractive index n_{eff} and change of effective refractive index Δn_{eff} along the transverse direction of the laser cavity.	12
Figure 1-9	Schematic diagram of an index-guided VCSEL with single oxide aperture.	14
Figure 1-10	Schematic diagram of a tapered waveguide buried heterostructure VCSEL (index-guided structure).	15
Figure 1-11	Schematic diagram of a hybrid-guided VCSEL using ion-implantation for gain-guiding and selective oxidation for index-guiding.	16
Figure 1-12	(a) The schematic structure of implant-apertured index-guided VCSEL (hybrid confinement), current confinement and photon confinement can be controlled independently. (b) The schematic of coupling relationship between transverse mode and gain spectrum.	17

Chapter 2

- Figure 2-1** The schematic of the overcoated VCSEL device using Ti/ITO 28
- Figure 2-2** The process procedures of proton-implanted VCSEL with transparent contact. 29
- Figure 2-3** The $L-I-V$ characteristics of a typical VCSEL with and without Ti/ITO transparent overcoating. 30
- Figure 2-4** Eye diagrams of the typical VCSEL device (a) without and (b) with Ti/ITO transparent overcoating operating at 2.125 Gb/s with 10 mA bias and 9 dB extinction ratio. The horizontal scale is 40 ps/div. 32
- Figure 2-5** The near-field emission patterns of the typical VCSEL device (a) without and (b) with Ti/ITO transparent overcoating at different injecting currents. 33

Chapter 3

- Figure 3-1** Schematic structure of a Si^+ -implant VCSEL. The Si implanted aperture is $13 \times 13 \mu\text{m}^2$ and proton implanted aperture is $30 \times 30 \mu\text{m}^2$. 38
- Figure 3-2** The schematic diagrams of fabricating processes. 39
- Figure 3-3** (a) Power versus current curves at 20 °C to 90 °C. The Si^+ -implanted VCSELs exhibit kink-free current-light output performance with threshold currents ~ 2.4 mA, and the slope efficiencies ~ 0.45 W/A. 40
- Figure 3-3** (b) Voltage versus current curves at 20 °C to 90 °C. The series resistance of more than 90% Si^+ -implanted VCSELs is within 40-45 Ohm indicating good re-growth interface. 41
- Figure 3-4** Distributions plot for threshold current and slope efficiency of Si^+ -implanted VCSEL. 42
- Figure 3-5** The optical output power spectrum of a Si^+ -implanted VCSEL driving at 3.5 mA ($1.45 \times I_{\text{th}}$). Inset is the spectrally resolved intensity pattern. 43
- Figure 3-6** Typical eye diagram of our VCSEL on TO-46 operating at 2.125 Gb/s (Fiber-Channel mask w. 20%-margin) with 7 mA bias and 9 dB extinction ratio at (a) 25 °C (b) 85 °C 44
- Figure 3-7** The WHTOL (85 °C/85 humidity) performance of Si^+ -implanted VCSEL chips. 45

Chapter 4

- Figure 4-1** Schematic structure of single-mode VCSEL. The O⁺-implanted aperture is 8 μm in diameter and the oxidation aperture is 10 μm in diameter. 58
- Figure 4-2** Figure 4-2 Device process flowchart. (a) The O⁺-implanted aperture was defined by photolithography with diameter of 8 μm. (b) The surface relief pattern with a diameter of 20 μm was etched by chemically assisted RIE (Reactive Ion Etching) 59
- Figure 4-3** (a) L-I-V curves, spectral characteristics and the near-field pattern of the O⁺-implanted VCSEL. The emission spectrum is obtained at 10 mA and the near-field pattern is obtained at 5 mA. They demonstrate that the O⁺ implanted VCSEL has a fundamental mode only over the full operating range. (b) L-I-V curves of the comparable conventional VCSEL. 60
- Figure 4-4** Characteristic eye diagram of (a) large-aperture single-mode VCSEL with diameter of 8μm; (b) conventional multi-mode VCSELs with diameter of 8μm, transmitted at 10Gb/s with a bias of 5mA and an extinct ratio of 6dB. 61

Chapter 5

- Figure 5-1** Schematic of the 850 nm PC-VCSEL. Note that the first generation PC-VCSEL structure has no oxide current aperture. The oxide aperture is added to the second generation devices for current confinement. 60
- Figure 5-2** The Schematic of lateral effective index variation provided by the photonic crystal 61
- Figure 5-3** V_{eff} parameters for $\gamma=0.06$, which correspond to etching depths of 17 pairs, are calculated. 63
- Figure 5-4** Schematic of PC-VCSEL. The hole depth of PC is 17 pairs out of 22 pairs of top DBR been etched off. The proton implantation position is 3 pairs of DBR layers above active region 64
- Figure 5-5** CW L-I-V characteristics and near-field image (inset) of a PC-VCSEL. The ratio (α/Λ) is 0.5 and the lattice constant Λ is 5 μm. 65
- Figure 5-6** Spectra of the proton-implanted (a) photonic crystal VCSEL with ratio (α/Λ) is 0.5 and the lattice constant Λ is 5 μm and (b) VCSEL without photonic crystal holes. 66
- Figure 5-7** Spectra of the proton-implanted VCSEL with photonic crystal ratio (α/Λ) is 0.5, seven-point defects and the lattice constant Λ 67

is 5 μm . The mesa of this device is 68 μm .

Figure 5-8 Divergent angles of the proton-implanted VCSEL (a) without and (b) with photonic crystal 68

Chapter 6

Figure 6-1 Schematic of photoelectrochemical oxidation setup. 74

Figure 6-2 L-I characteristics of conventional and PEC oxidized GaN-based LEDs. 76

