

ACKNOWLEDGEMENT

所有的花事、紅塵 雜亂和纏綿都收處書中

由線裝加上糊封 端整的擺在鋁製書架上

杜十三。花落

所有的實驗與資料尋找將會在這一本論文結束以後寫下休止符，耐心加上耐力是這幾年研究的主要支柱，除此之外若是沒有受到許多人的指導、鼓勵與照料，論文的豐富度將會大打折扣甚至無法完成。


最感謝的是我的指導教授 張豐志老師，無論是 張教授的身教或是言教，讓我在實驗室的這幾年裡受益良多。無時不刻地影響我對研究的態度及事業上待人接物的方式，令我永銘於心。吳厚德博士在論文方向、實驗技術的指導，一起體會研究學術的樂趣；特別感謝台灣大學 謝國煌教授、交通大學 吳建興教授 中興大學 吳震裕教授、高雄應用科技大學 陳樹仁教授以及高雄大學 王瑞琪教授等口試委員，有委員們的意見讓這本論文更臻完美。

實驗初期中許多儀器並不熟悉，幸好有陳憲偉學弟與邱俊毅學弟從旁協助讓實驗得以順利進行；特別感謝實驗室的夥伴洪辰睿博士、郭紹偉博士、黃志峰博士以及曾經在實驗室幫助過我的同學，使我在半工半讀的狀況下給我適時的支援，使研究的工作得以順利進行。另外也感謝地調所林燕初、TVBS 記者張嘉男、台大地質溫大任博士、高雄大學陳怡凱教授、吳政峰學長以及我兩位姊姊吳佳珍、吳佩芬，這些人在這一段不算短的歲月適時的給我鼓勵。

最後感謝茹苦含辛的父母，我想告別學生身份以後他們會很高興的。

~這是一個過程，生命還有很多重要的標的等著實現~

吳奕德 2007/02/12



CONTENTS

Description	Page
TITLE.....	III
中文摘要.....	IV
ABSTRACT.....	VII
ACKNOWLEDGEMENT.....	X
CONTENTS.....	XI
TABLE CONTENTS.....	XIII
FIGURE CONTENTS.....	XIV
Chapter I	
Introduction.....	1
1 Background of Infrared Spectroscopy.....	1
1-1 Basic Theory.....	1
1-2. Interpreting the Spectrum.....	3
1-3. Qualitative Analysis.....	4
1-4. Quantitative Analysis.....	5
1-5. Sample Preparation.....	5
1-6. Experimental Procedure.....	6
1-7. Example Spectrum.....	6
Chapter II	
Determination of the Crystallinity of Syndiotactic Polystyrene using FTIR	
Spectrum.....	11
2-1 Introduction.....	11
2-2 Material and Experimental Section.....	13
2-3 Results and Discussion.....	15
2-3-1 Infrared Spectra of the Bulk s-PS Ranging from 940 to 820 cm ⁻¹	15
2-3-2 Quantitative Measurement of Crystallinity on α - and β -crystals.....	17
2-3-3 Crystallization Processes of α - and β -crystals.....	19
2-4 Conclusions.....	21
2-5 Reference.....	22
Chapter III	
Characterization of Crystallization in Syndiotactic Polystyrene (s-PS) Thin Film	
Samples.....	34
3-1 Introduction.....	34
3-2 Experimental.....	35
3-3 Results and Discussion.....	37
3-4 Conclusions.....	41
3-5 Reference.....	42
Chapter IV	
The Interaction Behavior of Polymer Electrolytes Composed of Poly(vinyl	
pyrrolidone) and Lithium Perchlorate (LiClO ₄).....	48
4-1 Introduction.....	48
4-2 Experimental Section.....	50

4-2-1 Sample Preparation.....	50	
4-2-2 NMR Experiments.....	50	
4-2-3 Infrared Spectra.....	51	
4-3 Results and Discussions.....	52	
4-3-1 The Interaction Behavior of PVP Observed from Solid State NMR.....	52	
4-3-2 The Interaction Behavior of Li ⁺ Cation within PVP-LiClO ₄ Complex.....	55	
4-3-3 The Dissolved Behavior of the ClO ₄ ⁻ Anion.....	56	
4-3-4 The Formation of PVP-LiClO ₄ Salt Complex.....	58	
4-4 Conclusions.....	60	
4-5 References and Notes.....	61	
 Chapter V		
Determination of the Interaction within Polyester-Based Solid Polymer Electrolyte Using FTIR Spectroscopy.....	74	
5-1 Introduction.....	74	
5-2 Experimental Section.....	76	
5-2-1 Material.....	76	
5-2-2 Beer-Lambert's Law.....	77	
5-2-3 Sample Preparation and Infrared Spectroscopy.....	77	
5-3 Results and Discussions.....	79	
5-3-1 Infrared Spectra of the C=O Absorption Ranging from 1800 to 1650 cm ⁻¹	79	
5-3-2 Quantitative Measurement of Interaction Behavior on Polymer Electrolyte.....	80	
5-3-3 The Interaction between Li ⁺ Ion and C=O of Polymer Electrolytes.....	83	
5-4 Conclusions.....	86	
5-5 Reference.....	87	
 Chapter VI General Conclusions.....		100
Author.....	103	
Publications.....	104	

TABLE CONTENTS

Description	Page
Table 2-1 the specific characterized absorbance of s-PS in IR spectrum ranging from 940~820 cm ⁻¹	24
Table 2-2 Curve-fitting results of the ranging 865~820 cm ⁻¹ of s-PS IR spectra.	25
Table 2-3 The results of curve-fitting ranging between 865 and 820 cm ⁻¹ , crystallinity of melt-crystallized s-PS with various isothermal duration at 240 °C obtained from Figure 2-4.....	26
Table 2-4 The results of curve-fitting ranging between 865 and 820 cm ⁻¹ , crystallinity of cold-crystallized s-PS with various isothermal duration at 240 °C obtained from Figure 2-5.....	27
Table 3-1 the specific characterized absorbances of s-PS in IR spectra ranging from 940~820 cm ⁻¹	43
Table 3-2 The results of curve-fitting ranging between 865 and 820 cm ⁻¹ , absolute crystallinity of melt-crystallized and cold-crystallized s-PS at 264 °C for 240 min, results form Figure 3-2j and Figure 3-3h.....	44
Table 4-1 Observed Frequencies and Assignments of Infrared Bands of PVP-LiClO ₄ Complex, the [Li : O] = 0.056, in a Cast Film at 140 °C	64
Table 4-2 Curve-Fitting Data of Infrared Spectra of C=O Stretching Region of PVP/LiClO ₄ Complexes with Various Compositions at 140 °C	65
Table 5-1 Curve fitting and calculation results of FTIR spectra of PEA, PBA, PHA, and PCL in low Li ⁺ concentration of 1, 2 and 3 wt%.....	89
Table 5-2 Curve fitting of FTIR spectra of PEA, PBA, PHA, and PCL blended with LiClO ₄ from 5 wt% to 45 wt%.....	90
Table 5-3 summarizes that LiClO ₄ weight fraction vs. the equivalent fraction of “Li ⁺ bonded” C=O group results from Table 5-2 and Table 5-3 and Eq 5-2.....	91
Table 5-4 summarizes the Li ⁺ equivalent fraction (M ₂) Li ⁺ vs. “Li ⁺ bonded” C=O group equivalent fraction.....	92

FIGURE CONTENTS

Description:	Page
Figure 2-1 The characteristic infrared band of neat s-PS ranging from 940 to 820 cm^{-1} (a) quenched s-PS; (b) melt-crystallized s-PS at 240 $^{\circ}\text{C}$ for 240 min; (c) sample in figure 2-1b heating scan up to 264 $^{\circ}\text{C}$ from 30 $^{\circ}\text{C}$ with 10 $^{\circ}\text{C}/\text{min}$, then quenched by liquid nitrogen.....	28
Figure 2-2 FTIR spectra of s-PS <i>bulk</i> samples ranging from 940 to 820 cm^{-1} having cooled at various rates from -1 $^{\circ}\text{C}/\text{min}$ to -100 $^{\circ}\text{C}/\text{min}$. (a) -1; (b) -5; (c) -10; (d) -40; (e) -100 $^{\circ}\text{C}/\text{min}$, the dashed lines represent the result of curve-fitting of figure 2-2e ranging between 865 and 820 cm^{-1}	29
Figure 2-3 FTIR spectra of (a) quenched; (b) cold-crystallized; (c) melt-crystallized s-PS <i>thin</i> film sample at 240 $^{\circ}\text{C}$ for arbitrary duration using the same s-PS sample.....	30
Figure 2-4 FTIR spectra of melt-crystallized isothermally s-PS <i>thin</i> film sample at 240 $^{\circ}\text{C}$ for (a)2; (b) 6; (c) 10; (d) 60; and (e) 240 min.....	31
Figure 2-5 FTIR spectra of cold-crystallized isothermally s-PS <i>thin</i> film at 240 $^{\circ}\text{C}$ for (a)2; (b) 4; (c) 6; (d) 10; (e) 60; and (f) 240 min.....	32
Figure 2-6 Relationship of crystallinity and crystallization duration for exclusive (a) α -; and (b) β -crystal which isothermally crystallized at 240 $^{\circ}\text{C}$	33
Figure 3-1 IR spectra of s-PS (a) <i>bulk</i> sample, cooling from 320 $^{\circ}\text{C}$ to 30 $^{\circ}\text{C}$ with rate of -10 $^{\circ}\text{C}/\text{min}$; (b) <i>bulk</i> sample, heated up the quenched sample to 264 $^{\circ}\text{C}$ from 30 $^{\circ}\text{C}$ with scanning rate of 10 $^{\circ}\text{C}/\text{min}$; and (c) thin film sample, heated up the quenched sample to 264 $^{\circ}\text{C}$ from 30 $^{\circ}\text{C}$ with scanning rate of 10 $^{\circ}\text{C}/\text{min}$	45
Figure 3-2 IR spectra of melt-crystallized s-PS <i>thin</i> film at 264 $^{\circ}\text{C}$ for (a) 0 min; (b) 3 min; (c) 6 min; (d) 10 min; (e) 20 min; (f) 30 min; (g) 40 min; (h) 50 min; (i) 60 min; (j) 240 min durations ranging from 940~820 cm^{-1} . (Upper-right corner exhibits the curve-fitting ranging between 865 and 820 cm^{-1} for Figure 3-2j.).....	46
Figure 3-3 IR spectra of the cold-crystallized s-PS <i>thin</i> film at 264 $^{\circ}\text{C}$ for (a) 3 min; (b) 6 min; (c) 10 min; (d) 20 min; (e) 30 min; (f) 40 min; (g) 60 min; (h) 240 min durations ranging from 940~820 cm^{-1} . (Upper-right corner exhibits the curve-fitting ranging between 865 and 820 cm^{-1} for Figure 3-3h.).....	47

Figure 4-1 (a) Scaled ^{13}C CP/MAS NMR spectra region of LiClO ₄ -PVP complex ranging from 185 to 170 ppm, the [Li : O] equivalent ratio (a) = 0; (b) = 0.056; (c) = 0.337	66
Figure 4-1 (b) Scaled ^{13}C CP/MAS NMR spectra region of LiClO ₄ -PVP complex ranging from 50 to 16 ppm, the [Li : O] equivalent ratio (a) = 0; (b) = 0.056; (c) = 0.337.....	67
Figure 4-2 Infrared spectrum of PVP/LiClO ₄ ([Li : O] equivalent ratio = 0.056) complex in the spectral region between 3500 and 1000 cm ⁻¹ at 140 °C	68
Figure 4-3 Mid-Infrared spectra region from 1350 to 1225 cm ⁻¹ with various LiClO ₄ salt concentration at 140 °C , the [Li : O] equivalent ratio (a) = 0; (b) = 0.056; (c) = 0.337.....	69
Figure 4-4 Infrared spectra of C=O stretching region of PVP/LiClO ₄ complex at 140 °C , the [Li : O] equivalent ratio (a) = 0; (b) = 0.056; (c) = 0.112; (d) = 0.169; (e) = 0.225; (f) = 0.281; (g) = 0.337.....	70
Figure 4-5 The dependence of “free” and “complexed” C=O band on LiClO ₄ salt concentration. (a) “free”; (b) the “primary complexed”; and (c) the “secondary complexed” C=O band.....	71
Figure 4-6 Mid-Infrared spectra region from 1200 to 950 cm ⁻¹ PVP/LiClO ₄ complex with various LiClO ₄ salt concentration at 140 °C , the [Li : O] equivalent ratio (a) = 0; (b) = 0.056; (c) = 0.112; (d) = 0.169; (e) = 0.225; (f) = 0.281; (g) = 0.337.....	72
Figure 4-7 Schematic drawing of three types of the ionic association of polymer electrolytes—PVP/LiClO ₄ complex.....	73
Figure 5-1 The characteristic infrared band of (a) pure PEA; and LiClO ₄ 5wt% blend with (b) PEA; (c) PBA; (d) PHA; (e) PCL ranging from 1800~1650 cm ⁻¹ at 80 °C.....	93
Figure 5-2 FTIR spectra of PEA/LiClO ₄ blend ranging from 1800 to 1650 cm ⁻¹ with various LiClO ₄ content. (a) 1 wt%; (b) 2 wt%; (c) 3 wt% at 80 °C . (Dash line: result of Figure 2c curve fitting ranging from 1800 to 1650 cm ⁻¹	94
Figure 5-3 FTIR of spectra of (a) PEA/LiClO ₄ (b) PBA/LiClO ₄ (c) PHA/ LiClO ₄ (d) PCL/LiClO ₄ ranging from 1800 to 1650 cm ⁻¹ with increasing LiClO ₄ content up to 5 wt%(1%, 3% and 5%) at 80 °C	95
Figure 5-4 FTIR spectra of (a) PEA/LiClO ₄ , (b) PBA/ LiClO ₄ , (c) PHA/LiClO ₄ and (d) PCL/LiClO ₄ blends ranging from 1800 to 1650 cm ⁻¹ with the increase of LiClO ₄ content ranging from 10 wt% to 45 wt% at 80 °C	96

Figure 5-5 the relation of “Li ⁺ bonded” C=O equivalent fraction and LiClO ₄ weight content (wt%) for four series polymer electrolyte blends. (■: PEA; ●: PBA; ▲: PHA; ▼: PCL).....	97
Figure 5-6 the relation of “Li ⁺ bonded” C=O equivalent fraction and Li ⁺ equivalent fraction for four series polymer electrolyte blends. (■: PEA; ●: PBA; ▲: PHA; ▼: PCL).....	98
Figure 5-7 The semi-log relation of “Li ⁺ bonded” C=O equivalent fraction and Li ⁺ equivalent fraction for four series polymer electrolyte blends. (■: PEA; ●: PBA; ▲: PHA; ▼: PCL).....	99

