

## List of Figures

- Fig. 1 A schematic drawing of the ordering temperatures  $T_c(B2)$  and  $T_c(D0_3+L2_1)$  and the miscibility gap of the  $Cu_{3-x}Mn_xAl$  alloy.....12
- Fig. 2 Schematic representation of the ordering sequence of the quenched  $Cu_{2.5}Mn_{0.5}Al$  alloy (vertically) and its isothermal decomposition (horizontally).....13
- Fig. 3 Optical micrographs of the as-quenched alloys. (a) through (d) are alloy A ( $Cu_{2.9}Mn_{0.1}Al$ ), B ( $Cu_{2.8}Mn_{0.2}Al$ ), C ( $Cu_{2.7}Mn_{0.3}Al$ ) and alloy D ( $Cu_{2.6}Mn_{0.4}Al$ ), respectively.....18
- Fig. 4 Electron micrographs of the as-quenched alloy A. (a) BF, (b) and (c) two SADPs. The zone axes of the  $D0_3$  phase,  $\gamma_1'$  martensite and internal twin are (b)  $[001]$ ,  $[10\bar{1}]$  and  $[\bar{1}01]$ , (c)  $[111]$ ,  $[2\bar{1}0]$  and  $[\bar{2}10]$ , respectively ( $\underline{hkl}$ =  $D0_3$  phase,  $hkl$ =  $\gamma_1'$  martensite,  $hkl_T$ =internal twin), (d)  $(\bar{1}\bar{2}1)$   $\gamma_1'$  martensite DF.....22

Fig. 5 Electron micrographs of the as-quenched alloy B. (a) BF, (b) and (c) two SADPs. The zone axes of the  $D0_3$  phase are (b)  $[001]$  and (c)  $[110]$ , respectively ( $\underline{hkl}$ =  $D0_3$  phase,  $hkl$ = L-J phase,), (d) and (e)  $(002)$  and  $(\bar{1}11)$   $D0_3$  DF, respectively, (f)  $(0\bar{2}0)$  L-J DF.....26

Fig. 6 Electron micrographs of the as-quenched alloy C. (a) BF, (b) and (c) two SADPs. The zone axes of the  $D0_3$  phase are (b)  $[001]$  and (c)  $[110]$ , (d) and (e)  $(002)$  and  $(\bar{1}11)$   $D0_3$  DF, respectively, (f)  $(0\bar{2}0)$  L-J DF.....30

Fig. 7 Electron micrographs of the as-quenched alloy D. (a) BF, (b) SADP. The zone axes of the matrix are  $[001]$ , ( $\underline{hkl}$ =  $D0_3 + L2_1$  phase,  $hkl$ = L-J phase,) (c) and (d)  $(002)$  and  $(\bar{1}11)$   $D0_3$  DF, respectively, (e)  $(0\bar{2}0)$  L-J DF.....35