

# Contents

<b>Chinese Abstract</b>	<b>I</b>
<b>English Abstract</b>	<b>III</b>
<b>Acknowledgment (Chinese)</b>	<b>V</b>
<b>Content</b>	<b>VI</b>
<b>Table Captions</b>	<b>VIII</b>
<b>Figure Captions</b>	<b>IX</b>
<b>Chapter.1 Introduction</b>	
1.1 Background	1
1.2 Overview of grain control technologies	2
1.3 Introduction of diamond like carbon (DLC)	3
1.4 Laser crystallization mechanisms	3
1.5 Grain barrier carrier transport mechanism under high lateral field In poly-Si TFTs	4
1.5.1 Seto' s model	4
1.5.2 Possible grain boundary carrier transport mechanism in poly-Si TFTs	6
1.6 Motivation	9
1.7 Thesis outline	10
<b>Chapter.2 Experimental and Material Analysis</b>	
2.1 Instrument	12
2.1.1 Introduction of laser crystallization instrument	12
2.1.2 Introduction of Raman	13
2.2 Diamond like carbon characteristics	13
2.2.1 Diamond like carbon deposition	13

2.2.2	Material analysis	13
2.3	Amorphous silicon thin film with and without capped DLC crystallized by ELA	15
2.3.1	Sample fabrication and Laser irradiation	15
2.3.2	Material analysis	16
2.4	Crystallization mechanism for 1000A a-Si with heat retaining Layer of DLC	18
 <b>Chapter.3      Analysis of Kink Effect in Poly-Si TFTs</b>		
3.1	Possible kink effect related mechanisms	20
3.2	Device Fabrication	20
3.3	Parameter extracted method	21
3.4	Electrical characteristics	22
3.4.1	Different laser crystallized quality	22
3.4.2	Different bias voltage	24
3.4.3	Different laser crystallization	24
3.4.4	Kink current	25
 <b>Chapter.4      Conclusion</b>		
	Reference	30
	Tables	
	Figures	

## Table Captions

Table I. The average grain size of different laser energy (scan pitch fixed to 2 $\mu$ m)

Table II The trap density of ELA (380mJ/cm<sup>2</sup>) and SSL with laser energy density of 415mJ/cm<sup>2</sup> to 507mJ/cm<sup>2</sup>.



## Figure Caption

### Chapter 1

- Fig.1-4-1 The simple schematic diagram of melted silicon (a) flow from the edge to the middle (b) flow from the middle to the edge during crystallization
- Fig.1-5-1 The distribution of the charges in poly-Si
- Fig.1-5-2 The relationship between energy barrier height and gate voltage
- Fig.1-5-3 The output characteristic of device before and after passivation
- Fig.1-5-4 The “activation energy” is from this charged trap energy level to the conduction band edge

### Chapter 2

- Fig.2-2-1 The reflectivity of DLC film. The thickness of DLC is  $100\text{nm}$
- Fig.2-2-2 The transmittance of DLC film. The thickness of DLC is  $100\text{nm}$
- Fig.2-2-3 The Raman spectrum of DLC before and after laser irradiated by 300 to  $500\text{mJ/cm}^2$
- Fig.2-2-4 The calculated absorptivity of DLC films before and after laser irradiation with laser energy density of 300 and  $500\text{mJ/cm}^2$
- Fig.2-3-1 The cross-section of sample A. The space between DLC pattern are 3,6,10,20,30,50 $\mu\text{m}$  and the length of DLC are 4,6,8,12,16,20,30,60 $\mu\text{m}$
- Fig.2-3-2 (a) The cross-section of sample B. (b) The cross-section of reference of sample B
- Fig.2-3-3 The optical picture, of sample A with the laser energy of (a)  $400\text{mJ/cm}^2$  (b)  $500\text{mJ/cm}^2$  (c)  $600\text{mJ/cm}^2$
- Fig.2-3-4 The AFM result of the region near the middle of the DLC patterns

Fig.2-3-5 SEM image of sample A with laser energy density of (a)  $400\text{mJ}/\text{cm}^2$  (b)  $500\text{mJ}/\text{cm}^2$  (c)  $600\text{mJ}/\text{cm}^2$

Fig.2-3-6 (a) The position of Raman irradiated (b) The Raman spectra of different position which is shown as (a)

Fig.2-3-7 The Raman result of sample A with the laser energy of (a)  $400\text{mJ}/\text{cm}^2$  (b)  $500\text{mJ}/\text{cm}^2$  (c)  $600\text{mJ}/\text{cm}^2$

Fig.2-3-8 The Raman spectra for sample B at the position of poly-silicon near DLC patterns with the laser energy of (a)  $500\text{mJ}/\text{cm}^2$  (b)  $600\text{mJ}/\text{cm}^2$  (c) The Raman spectra for the reference sample of sample B without DLC patterns

Fig.2-4-1 The schematic diagram of the proposed crystallization process

### Chapter 3

Fig.3-2-1 The cross-section of view of poly-Si TFT with self-align source/drain

Fig.3-3-1 The saturation voltage at various gate voltages can be defined from the “first” minimum points of the conductance

Fig.3-3-2 The kink current  $I_{\text{KINK}}$  can be evaluated by using the drain current at high drain voltage to minus the rectified saturation current, such that  $I_{\text{KINK}}=I_{\text{D}}-I_{\text{D,SAT}}$

Fig.3-3-3 Arrhenius plot of the drain current of TFT with different gate voltages and  $V_{\text{DS}}=0.1\text{V}$ . The slope of each line defines the activation energy at the grain boundary

Fig 3-3-4 The average trap density was extracted from slope of this plot

Fig.3-4-1 The model of grain boundary accelerated electron. The grain boundary barrier height is fixed. (a) carriers are accelerated by the grain boundary energy trop (b) larger grain size shows a gentler energy drop

- Fig.3-4-2 (a) The grain boundary barrier height with the laser energy density of  $415\text{mJ/cm}^2$  (b) The multiplication factor with the laser energy density of  $415\text{mJ/cm}^2$
- Fig.3-4-3 (a) The grain boundary barrier height with the laser energy density of  $438\text{mJ/cm}^2$  (b) The multiplication factor with the laser energy density of  $438\text{mJ/cm}^2$
- Fig.3-4-4 (a) The grain boundary barrier height with the laser energy density of  $507\text{mJ/cm}^2$  (b) The multiplication factor with the laser energy density of  $507\text{mJ/cm}^2$
- Fig.3-4-5 The average trap density of SSL with different grain sizes (from  $0.1\mu\text{m}$ - $1\mu\text{m}$ )
- Fig.3-4-6 The multiplication factor of laser energy density form  $415\sim 507\text{mJ/cm}^2$ . Multiplication factor decreases with the laser energy density increases
- Fig.3-4-7 The band diagram of the grain boundary accelerated electron affect by the drain voltage
- Fig 3-4-8 The multiplication factor increases with the drain voltage. And the larger laser energy density shows less serious kink effect.
- Fig.3-4-9 The multiplication factor is decreases with the gate voltage increases. Because of the effective lateral electric field lowering and the effective grain barrier height reduction
- Fig.3-4-10 The multiplication factor of different laser energy density for a fixed  $V_D - V_{D,SAT}$  value. The multiplication factor of a larger laser energy poly-Si film achieve a negligible small value faster
- Fig.3-4-11 The grain barrier height of ELA and SSL  $415\text{mJ/cm}^2$  silicon films. The grain barrier height of ELA is larger than the SSL  $415\text{mJ/cm}^2$  one

Fig.3-4-12 Under the same lateral electric field, the multiplication factor of ELA is larger than the one of SSL  $415\text{mJ}/\text{cm}^2$ .

Fig.3-4-13 The grain barrier height of ELA and SSL  $415\sim 507\text{mJ}/\text{cm}^2$ . The grain barrier height of SSL is smaller than ELA. And also the grain sizes with laser energy density of  $438\text{mJ}/\text{cm}^2$  and  $507\text{mJ}/\text{cm}^2$  are much larger than ELA.

Fig.3-4-14 The grain size of SSL  $438\text{mJ}/\text{cm}^2$  and  $507\text{mJ}/\text{cm}^2$  is larger than ELA and the grain barrier height is also small than ELA. So the multiplication factor of SSL  $438\text{mJ}/\text{cm}^2$  and  $507\text{mJ}/\text{cm}^2$  is much smaller than ELA's.

Fig.3-4-15 The kink current of SSL with laser energy density from  $415\text{mJ}/\text{cm}^2$  to  $507\text{mJ}/\text{cm}^2$

